

Congrui Jin

Department of Mechanical Engineering,
State University of New York at Binghamton,
Binghamton, NY 13902
e-mail: cjin@binghamton.edu

Marco Salvati¹

William E. Boeing Department of Aeronautics
and Astronautics,
University of Washington,
Seattle, WA 98195
e-mail: salvati@aa.washington.edu

Weixin Li

Department of Civil
and Environmental Engineering,
Northwestern University,
Evanston, IL 60208
e-mail: w.li@u.northwestern.edu

Gianluca Cusatis

Department of Civil and
Environmental Engineering,
Northwestern University,
Evanston, IL 60208
e-mail: g-cusatis@northwestern.edu

Elastic Microplane Formulation for Transversely Isotropic Materials

This contribution investigates the extension of the microplane formulation to the description of transversely isotropic materials such as shale rock, foams, unidirectional composites, and ceramics. Two possible approaches are considered: (1) the spectral decomposition of the stiffness tensor to define the microplane constitutive laws in terms of energetically orthogonal eigenstrains and eigenstresses and (2) the definition of orientation-dependent microplane elastic moduli. The first approach, as demonstrated previously, provides a rigorous way to tackle anisotropy within the microplane framework, which is reviewed and presented herein in a clearer manner; whereas the second approach represents an approximation which, however, makes the formulation of nonlinear constitutive equations much simpler. The efficacy of the second approach in modeling the macroscopic elastic behavior is compared to the thermodynamic restrictions of the anisotropic parameters showing that a significant range of elastic properties can be modeled with excellent accuracy. Further, it is shown that it provides a very good approximation of the microplane stresses provided by the first approach, with the advantage of a simpler formulation. It is concluded that the spectral stiffness decomposition represents the best approach in such cases as for modeling composites, in which accurately capturing the elastic behavior is important. The introduction of orientation-dependent microplane elastic moduli provides a simpler framework for the modeling of transversely isotropic materials with remarked inelastic behavior, as in the case, for example, of shale rock. [DOI: 10.1115/1.4034658]

1 Introduction

Quasi-brittle materials are defined as those materials that exhibit no or negligible plastic strain prior to failure [1]. The formation and growth of fracture process zone are considered to be responsible for both the softening behavior observed in the post-peak stress-strain curve and the development of plastic irreversible strains [2]. The presence of anisotropy in quasi-brittle materials is very common. For example, the response of rigid foams is usually anisotropic. During the foaming process, viscous forces cause the cells to be elongated in the rise direction, and the material response will be therefore stiffer in this direction [3]. A special case of anisotropy is transverse isotropy, which contains a plane of isotropy, implying that the material can be rotated with respect to the loading direction about one axis without measurable effect on material's response. Due to its high symmetry and relative simplicity in mathematical formulae, transversely isotropic medium has become one of the most studied anisotropic media in the literature. Fiber-reinforced composites with all fibers being in parallel can be regarded as transversely isotropic, and many sedimentary rocks, such as shales, slates, siltstones, claystones, and mudstones, are best described as transversely isotropic media with the symmetric axes perpendicular to bedding. Such bedding planes affect the strength and deformational behaviors of the rock with orientation to the applied stresses.

Elastic transverse isotropy is the subject of the present contribution which investigates the extension of the microplane formulation to this type of anisotropy. Two possible approaches are compared: (1) the spectral decomposition of the stiffness tensor to define the microplane constitutive laws in terms of energetically

orthogonal eigenstrains and eigenstresses and (2) the definition of orientation-dependent microplane elastic moduli.

2 Background of Microplane Model

The microplane model describes the material behavior at the mesoscopic scale by formulating the constitutive laws in terms of stress and strain vectors acting on individual microplanes of all possible orientations at a given material point [3–22], instead of using a traditional tensorial constitutive model. These microplanes may be imagined to represent damage planes or weak planes in the mesoscale structures, such as contact layers between aggregate pieces in concrete or defects in composite laminates.

The microplane concept has known a long history. The characterization of the material behavior on different material planes was first suggested by Mohr [23] in 1900. This idea was then advanced by Taylor [24] and applied to develop the slip theory of plasticity by Batdorf and Budiansky [25]. Later, it was extended by Bažant and his co-workers to model quasi-brittle materials exhibiting softening damage [4,5]. Since then, the microplane model for concrete has been studied extensively and evolved through several progressively improved versions [4–6, 8–13, and 18–21]. Numerous advantages of microplane models were reviewed in Brocca and Bažant [26] and Cusatis et al. [27]. The main appealing aspect of this approach is its conceptual simplicity, i.e., once the general algorithm for the relationship between microplane quantities and macroscopic tensors has been established, formulating a constitutive law is intuitive, since all the quantities involved always have an immediate physical meaning. Oriented phenomena, such as friction and cracking, can be realistically simulated. Besides, the microplane model automatically exhibits the vertex effect, which has not been captured by any usable tensorial models, and the interaction of microplanes accurately captures all the cross effects, such as shear dilatancy and pressure sensitivity. This also allows simulating damage-induced anisotropy quite simply. Despite the fact that the adoption of the

¹Corresponding author.

Contributed by the Applied Mechanics Division of ASME for publication in the JOURNAL OF APPLIED MECHANICS. Manuscript received August 11, 2016; final manuscript received September 1, 2016; published online October 5, 2016. Editor: Yonggang Huang.

microplane modeling approach is usually computationally expensive compared to the classical tensorial models, systems of millions of finite elements have been successfully solved using the microplane model for concrete [7]. Microplane models have also been developed for other complex materials such as rock [14], cemented soils [28], clay [15], rigid foam [3], fiber reinforced concrete [17], shape memory alloy [29], and fiber composites (prepreg laminates [27,30] and braided composites [31]). Finally, it is worth noting that the constitutive relations prescribed on the microplanes, which are lumped into a single material point in the microplane models, can also be used in an explicit mesoscale model on planes of various orientations separating the neighboring aggregates embedded in a cement mortar matrix, as it has been done in the recently developed lattice discrete particle model (LDPM) [32,33]. Inevitably, there are similarities between the constitutive relations of microplane models and those of LDPM.

However, most of the microplane and LDPM simulations have been focusing on the mechanical behavior of isotropic quasi-brittle materials, and there are only a few studies on the formulation for anisotropic quasi-brittle materials [3,15,27,34]. The formulation for anisotropy could be complex even in the elastic regime, as elasticity must be defined on the microplanes in order to model softening damage. Brocca et al. proposed a microplane formulation for stiff foam based on the assumption that the elastic moduli on the microplanes vary ellipsoidally as a function of the microplane orientation [3]. This approach cannot be used to correctly represent the mechanical properties of strongly anisotropic materials due to the fact that an exact correspondence in elasticity between tensorial macrostiffness and vectorial microstiffness cannot be obtained. A similar limitation exists in the microplane models developed for anisotropic clay [15,34]. As shown by Cusatis et al. [27], only the microplane formulation based on spectral decomposition of the stiffness tensor guarantees that an exact correspondence in elasticity between the microplane formulation and the tensorial formulation can be established. Although the spectral stiffness microplane model is the only known exact and rigorous approach for the anisotropic generalization of the microplane model, such a method becomes less appropriate for the simulation of the nonlinear and softening behaviors of quasi-brittle materials. Cusatis et al. managed to simulate the strain-softening damage and fracture mechanics aspects by using strain-dependent limits to provide bounds for the microplane stresses in each spectral mode [27], but it is not as convenient as directly using microplane normal stress and strain components. This, along with the fact that too many parameters need to be identified in the calibration procedure, renders the method unwieldy in practice, and therefore there remains a scientific challenge to relate the macroscopic response of anisotropic quasi-brittle materials to the elastic properties of its underlying microstructure.

Even for the simulation of the elasticity of isotropic quasi-brittle materials, as it was pointed out by Bažant et al. [9] and Cusatis et al. [32], the microplane formulation without volumetric-deviatoric split of the strain cannot cover the entire

range of thermodynamically acceptable Poisson's ratios ($-1 \leq \nu \leq 0.5$): Poisson's ratio is restricted to the range from -1 to 0.25 . Although the full Poisson's ratio range can be obtained by introducing the volumetric-deviatoric decomposition of the normal strain [35], this complicates severely the damage formulation. The same issue exists for the simulation of anisotropic quasi-brittle materials, and there still exists no microplane model without spectral decomposition that is capable of giving the complete range of thermodynamically admissible Poisson's ratio. In this study, the possibility of formulating a microplane model for transversely isotropic quasi-brittle materials based on the assumption that the elastic moduli on the microplanes vary with the microplane orientation is investigated in detail, and the ranges of Poisson's ratios produced by the model are compared with the full Poisson's ratio range obtained from the thermodynamic restrictions and the microplane spectral stiffness formulation.

3 Thermodynamic Restrictions on Elastic Constants of Transversely Isotropic Materials

The elastic stress-strain relation of an anisotropic material can be written in tensorial notation as $\sigma_{ij} = E_{ijkl}\varepsilon_{kl}$, where the indices refer to Cartesian coordinates x_i ($i = 1, 2, 3$); σ_{ij} and ε_{ij} are the second-order stress and strain tensors, respectively. They are symmetric and their symmetry enables their contraction into six-dimensional vectors $\boldsymbol{\sigma}$ and $\boldsymbol{\varepsilon}$. Similarly, the internal and external symmetries of the fourth-order stiffness tensor E_{ijkl} allow its contraction into a 6×6 matrix \mathbf{E} . The following rules contract a pair of indices into a single index: $11 \rightarrow 1, 22 \rightarrow 2, 33 \rightarrow 3, (23, 32) \rightarrow 4, (13, 31) \rightarrow 5, \text{ and } (12, 21) \rightarrow 6$. Therefore, in matrix notation, one can write $\boldsymbol{\sigma} = \mathbf{E}\boldsymbol{\varepsilon}$ where $\boldsymbol{\sigma} = [\sigma_{11}, \sigma_{22}, \sigma_{33}, \sqrt{2}\sigma_{23}, \sqrt{2}\sigma_{13}, \sqrt{2}\sigma_{12}]^T$, $\boldsymbol{\varepsilon} = [\varepsilon_{11}, \varepsilon_{22}, \varepsilon_{33}, \sqrt{2}\varepsilon_{23}, \sqrt{2}\varepsilon_{13}, \sqrt{2}\varepsilon_{12}]^T$, and the matrix \mathbf{E} is defined accordingly. The foregoing definitions of six-dimensional vectors are known as the Kelvin notation [36]. The factor $\sqrt{2}$ assures that both the stiffness tensor and its column matrix have the same norm, given by the sum of the squares of their elements.

As an anisotropic medium of the highest symmetry, i.e., hexagonal symmetry, transversely isotropic medium possesses a rotational symmetry axis and the least number of independent elastic constants (five in total). For the case of transverse isotropy with isotropy in the 1-2 plane, as shown in Fig. 1(a), the elastic compliance matrix, $\mathbf{C} = \mathbf{E}^{-1}$, is given by

$$\mathbf{C} = \begin{bmatrix} 1/E & -\nu/E & -\nu'/E' & 0 & 0 & 0 \\ -\nu/E & 1/E & -\nu'/E' & 0 & 0 & 0 \\ -\nu'/E' & -\nu'/E' & 1/E' & 0 & 0 & 0 \\ 0 & 0 & 0 & 1/(2G) & 0 & 0 \\ 0 & 0 & 0 & 0 & 1/(2G) & 0 \\ 0 & 0 & 0 & 0 & 0 & (1+\nu)/E \end{bmatrix} \quad (1)$$

where E' and E are Young's moduli in the longitudinal and transverse directions, respectively, G is out-of-plane shear modulus, ν' and ν are Poisson's ratios in the longitudinal and transverse directions, respectively.

It is well known that a necessary and sufficient condition for the work done on an elastic material to be strictly positive is that the matrix \mathbf{C} be symmetric and positive definite [37]. If the work done on a material is not positive, then useful work could be extracted from the material. This would be a violation of established thermodynamic principles. A necessary and sufficient condition for a symmetric matrix to be positive definite is that all determinants formed from it be positive. In the case of a transversely isotropic material, applying the conditions of positive definiteness to the compliance matrix \mathbf{C} , one can show that the following inequalities must be satisfied by the elastic constants:




Fig. 1 (a) Coordinate system for transversely isotropic materials and (b) spherical coordinate system

$$-1 < \nu < 1 \quad (2)$$

$$-\sqrt{E'/E} < \nu' < \sqrt{E'/E} \quad (3)$$

$$\nu < 1 - 2(\nu')^2 (E/E') \quad (4)$$

By making use of these equations, one can find the lower and upper bounds of ν' for every possible value of ν with different values of E/E' , as plotted in Fig. 2.

4 Microplane Model Formulation With Different Types of Constraints

At the microstructural level, nonlinear and inelastic phenomena often occur on planes of a certain specific orientation, and thus the constitutive law characterizing the mechanical behavior is best described by a relationship between stress and strain vectors acting on a generic plane of arbitrary spatial orientation. These microplanes can be imagined as the tangent planes of a unit sphere surrounding every point in the three-dimensional space [27].




Fig. 2 The contour plot of t for each case. The results are compared with the thermodynamic restrictions on elastic constants of transversely isotropic materials. The figure appears in color in the electronic version of this article.

There are two different classes of microplane models: the kinematically constrained and the statically constrained [3]. In the kinematically constrained microplane model, the strain vector on each microplane is the projection of the macroscopic strain tensor. Using Kelvin notation, one can write $\varepsilon_P = \mathbf{P}\varepsilon$ where $\varepsilon_P = [\varepsilon_N, \varepsilon_M, \varepsilon_L]^T$ is the microplane strain vector, with ε_N being the normal strain component, and ε_M and ε_L being the shear strain components, respectively. The matrix \mathbf{P} can be written as:

$$\mathbf{P} = \begin{bmatrix} N_{11} & N_{22} & N_{33} & \sqrt{2}N_{23} & \sqrt{2}N_{13} & \sqrt{2}N_{12} \\ M_{11} & M_{22} & M_{33} & \sqrt{2}M_{23} & \sqrt{2}M_{13} & \sqrt{2}M_{12} \\ L_{11} & L_{22} & L_{33} & \sqrt{2}L_{23} & \sqrt{2}L_{13} & \sqrt{2}L_{12} \end{bmatrix} \quad (5)$$

which collects the components of the tensors $N_{ij} = n_i n_j$, $M_{ij} = (m_i n_j + m_j n_i)/2$ and $L_{ij} = (l_i n_j + l_j n_i)/2$, where n_i , m_i , and l_i are local Cartesian coordinate vectors on the generic microplane, with n_i being normal. If the microplane orientation is defined by spherical angles θ and ϕ , as shown in Fig. 1(b), then $n_1 = \sin \theta \cos \phi$, $n_2 = \sin \theta \sin \phi$, and $n_3 = \cos \theta$, and one can choose $m_1 = \cos \theta \cos \phi$, $m_2 = \cos \theta \sin \phi$, and $m_3 = -\sin \theta$, which gives $l_1 = -\sin \phi$, $l_2 = \cos \phi$, and $l_3 = 0$. Once the strain components on each microplane are obtained, the stress components are updated through microplane constitutive laws, which can be expressed in an algebraic or differential form. If the kinematic constraint is imposed, in general, the microplane stress components do not coincide with the projections of the macroscopic stress tensor, i.e., $\sigma_P \neq \mathbf{P}\sigma$. Thus, static equivalence or equilibrium between the microplane stress components and macroscopic stress tensor must be enforced by other means. This is accomplished by applying the principle of virtual work, which leads to

$$\sigma = \frac{3}{2\pi} \int_{\Omega} \mathbf{P}^T \sigma_P d\Omega \quad (6)$$

where Ω is the surface of a unit hemisphere.

The kinematic constraint was proposed to stabilize the system of softening microplanes, since the statically constrained microplane models, similar to the classic Taylor models developed for metals and nonsoftening soils, can be only used for hardening plasticity. It is possible to formulate the microplane model such that a kinematic constraint for the strains coexists with a static constraint for the stresses. When this happens, the model is said to have a double constraint. As proved by Cusatis et al. [27], such a double constraint exists in the elastic regime if and only if microplane elasticity is formulated through the spectral decomposition of the stiffness or compliance matrices.

5 Spectral Stiffness Microplane Model

By using the spectral decomposition theorem [27,38–40], the stiffness matrix \mathbf{E} can be decomposed as $\mathbf{E} = \sum_I \lambda_I \mathbf{E}_I$ where λ_I are the eigenvalues of \mathbf{E} , and \mathbf{E}_I define a set of matrices constructed from the eigenvectors of \mathbf{E} as $\mathbf{E}_I = \sum_n \phi_{In} \phi_{In}^T$, where ϕ_{In} is the normalized eigenvector associated with the eigenvalue λ_I of multiplicity n so that $\phi_{In}^T \mathbf{E} \phi_{In} = \lambda_I$. The following conditions hold for the matrix \mathbf{E} : $\sum_I \mathbf{E}_I = \mathbf{1}$, $\mathbf{E}_I \mathbf{E}_J = \mathbf{E}_I$, and $\mathbf{E}_I \mathbf{E}_J = \mathbf{0}$ ($I \neq J$). \mathbf{E}_I decomposes the stress and strain vectors into energetically orthogonal modes, which are called eigenstresses and eigenstrains, as $\varepsilon_I = \mathbf{E}_I \varepsilon$ and $\sigma_I = \mathbf{E}_I \sigma$, respectively, where $\sigma = \sum_I \sigma_I$, $\varepsilon = \sum_I \varepsilon_I$, and $\sigma_I = \lambda_I \varepsilon_I$. In a similar manner, one can also decompose the stress and strain vectors into microplane eigenstresses and microplane eigenstrains as $\varepsilon_{PI} = \mathbf{P}_I \varepsilon$ and $\sigma_{PI} = \mathbf{P}_I \sigma$, respectively, where $\mathbf{P}_I = \mathbf{P} \mathbf{E}_I$ [27]. Finally, in the elastic regime, the microplane eigenstresses are proportional to the microplane eigenstrains through the associated eigenvalue, that is, $\sigma_{PI} = \lambda_I \varepsilon_{PI}$.

For the case of transverse isotropy, the eigenvalues of the compliance matrix \mathbf{C} , which are the reciprocal of the eigenvalues λ_I of the stiffness matrix \mathbf{E} , can be expressed as [27,39]

$$\lambda_1^{-1} = \frac{1+\nu}{E}, \lambda_2^{-1} = \frac{1-\nu}{2E} + \frac{1}{2E'} \\ - \left[\left(\frac{1-\nu}{2E} - \frac{1}{2E'} \right)^2 + \frac{2\nu'^2}{E'^2} \right]^{1/2}, \lambda_3^{-1} = \frac{1-\nu}{2E} + \frac{1}{2E'} \\ + \left[\left(\frac{1-\nu}{2E} - \frac{1}{2E'} \right)^2 + \frac{2\nu'^2}{E'^2} \right]^{1/2}, \text{ and } \lambda_4^{-1} = \frac{1}{2G}$$

and the corresponding \mathbf{E}_I can be expressed as

$$\mathbf{E}_1 = \begin{bmatrix} 1/2 & -1/2 & 0 & 0 & 0 & 0 \\ -1/2 & 1/2 & 0 & 0 & 0 & 0 \\ 0 & 0 & 0 & 0 & 0 & 0 \\ 0 & 0 & 0 & 0 & 0 & 0 \\ 0 & 0 & 0 & 0 & 0 & 0 \\ 0 & 0 & 0 & 0 & 0 & 0 \end{bmatrix} \quad (7)$$

$$\mathbf{E}_2 = \begin{bmatrix} c^2/2 & c^2/2 & cs/\sqrt{2} & 0 & 0 & 0 \\ c^2/2 & c^2/2 & cs/\sqrt{2} & 0 & 0 & 0 \\ cs/\sqrt{2} & cs/\sqrt{2} & s^2 & 0 & 0 & 0 \\ 0 & 0 & 0 & 0 & 0 & 0 \\ 0 & 0 & 0 & 0 & 0 & 0 \\ 0 & 0 & 0 & 0 & 0 & 0 \end{bmatrix} \quad (8)$$

$$\mathbf{E}_3 = \begin{bmatrix} s^2/2 & s^2/2 & -cs/\sqrt{2} & 0 & 0 & 0 \\ s^2/2 & s^2/2 & -cs/\sqrt{2} & 0 & 0 & 0 \\ -cs/\sqrt{2} & -cs/\sqrt{2} & c^2 & 0 & 0 & 0 \\ 0 & 0 & 0 & 0 & 0 & 0 \\ 0 & 0 & 0 & 0 & 0 & 0 \\ 0 & 0 & 0 & 0 & 0 & 0 \end{bmatrix} \quad (9)$$

$$\mathbf{E}_4 = \begin{bmatrix} 0 & 0 & 0 & 0 & 0 & 0 \\ 0 & 0 & 0 & 0 & 0 & 0 \\ 0 & 0 & 0 & 0 & 0 & 0 \\ 0 & 0 & 0 & 1 & 0 & 0 \\ 0 & 0 & 0 & 0 & 1 & 0 \\ 0 & 0 & 0 & 0 & 0 & 0 \end{bmatrix} \quad (10)$$

where $c = \cos \omega$, $s = \sin \omega$, and $\tan 2\omega = [-2\sqrt{2}\nu'/E'] / [(1-\nu)/E - 1/E']$.

As a generalization of the volumetric-deviatoric decomposition, the spectral stiffness microplane model is the only exact and rigorous approach for the anisotropic generalization of the microplane model, but it becomes unwieldy for the simulation of the nonlinear and softening behaviors of quasi-brittle materials. This is because various nonlinear and softening laws must be formulated for the different spectral modes and for their interaction. Furthermore, the use in the nonlinear regime of the spectral deformation modes that are derived from the elastic stiffness matrix can be questioned from a theoretical point of view. In many cases, it is easier to formulate nonlinear constitutive equations, especially for fracture and damage, with reference to the total microplane stresses and strains. To directly use normal stress and strain components, a microplane formulation based on the assumption that the elastic moduli on the microplanes vary with the microplane orientation is more convenient. This type of elastic formulation is discussed in Sec. 6.

6 Microplane Model with Orientation Dependent Moduli

To capture the macroscopic response of anisotropic materials, Brocca et al. [3] proposed a microplane formulation based on the assumption that the elastic moduli on the microplanes vary as functions of the microplane orientation, that is, $E_i = E_i(\phi, \theta)$,

where subscript $i = N, M, L$ labels the components of the microplane strain and stress vectors. Furthermore, for transversely isotropic materials, one can assume that the moduli are functions of θ only. By integrating the microplane elastic energy over the unit hemisphere, one can obtain:

$$\begin{aligned} \frac{1}{2} \boldsymbol{\sigma}^T \mathbf{E}^* \boldsymbol{\sigma} = W &= \frac{3}{2\pi} \int_{\Omega} \frac{1}{2} \boldsymbol{\sigma}_p^T \mathbf{E}_p \boldsymbol{\sigma}_p d\Omega \\ &= \frac{1}{2} \boldsymbol{\sigma}^T \left[\frac{3}{2\pi} \int_{\Omega} \mathbf{P}^T \mathbf{E}_p \mathbf{P} d\Omega \right] \boldsymbol{\sigma} \Rightarrow \mathbf{E}^* = \frac{3}{2\pi} \int_{\Omega} \mathbf{P}^T \mathbf{E}_p \mathbf{P} d\Omega \end{aligned} \quad (11)$$

where $\mathbf{E}_p = \text{diag}(E_i)$.

The objective of this study is to investigate the form of the function of $E_i(\theta)$ which gives the maximum range of Poisson's ratios. The following four cases are studied. The first is case A, characterized by a linear variation with θ :

$$\begin{aligned} E_N &= (a_1 - a_2) \frac{2}{\pi} \theta + a_2; \quad E_M = (a_3 - a_4) \frac{2}{\pi} \theta + a_4; \\ E_L &= (a_3 - a_4) \frac{2}{\pi} \theta + a_4 \end{aligned} \quad (12)$$

The second case, case B, makes use of trigonometric functions:

$$\begin{aligned} E_N &= a_1 \sin^2 \theta + a_2 \cos^2 \theta; \quad E_M = a_3 \sin^2 \theta + a_4 \cos^2 \theta; \\ E_L &= a_3 \sin^2 \theta + a_4 \cos^2 \theta \end{aligned} \quad (13)$$

The third case, case C, uses the inverse of the functions in case B:

$$\begin{aligned} E_N &= (a_1 \sin^2 \theta + a_2 \cos^2 \theta)^{-1}; \quad E_M = (a_3 \sin^2 \theta + a_4 \cos^2 \theta)^{-1}; \\ E_L &= (a_3 \sin^2 \theta + a_4 \cos^2 \theta)^{-1} \end{aligned} \quad (14)$$

where a_i ($i = 1, 2, 3, 4$) are positive unknown parameters. In both case A and case B, $E_N|_{\theta=0} = a_2$, $E_N|_{\theta=\pi/2} = a_1$, $E_L|_{\theta=0} = E_M|_{\theta=0} = a_4$, and $E_L|_{\theta=\pi/2} = E_M|_{\theta=\pi/2} = a_3$. In case C, instead, one has $E_N|_{\theta=0} = 1/a_2$, $E_N|_{\theta=\pi/2} = 1/a_1$, $E_L|_{\theta=0} = E_M|_{\theta=0} = 1/a_4$, and $E_L|_{\theta=\pi/2} = E_M|_{\theta=\pi/2} = 1/a_3$. In all the cases, the condition $a_i > 0$ ($i = 1, 2, 3, 4$) ensures that $E_i > 0$ ($i = N, M, L$).

Finally, the fourth case, case D, assumes independent modulus values at each microplane orientation. For the most commonly adopted quadrature formula with 37 microplanes [41,42], this approach involves the values of E_N and E_M at eight different θ : $\theta_1 = 0$, $\theta_2 = 0.1\pi$, $\theta_3 = 0.157\pi$, $\theta_4 = 0.25\pi$, $\theta_5 = 0.304\pi$, $\theta_6 = 0.391\pi$, $\theta_7 = 0.4\pi$, and $\theta_8 = 0.5\pi$. Hence, in this case, Young's moduli, E and E' , and Poisson's ratios, ν and ν' , for the transversely isotropic material depend on 16 parameters: $E_M(\theta_1)$, $E_M(\theta_2)$, $E_M(\theta_3)$, $E_M(\theta_4)$, $E_M(\theta_5)$, $E_M(\theta_6)$, $E_M(\theta_7)$, $E_M(\theta_8)$, $E_N(\theta_1)$, $E_N(\theta_2)$, $E_N(\theta_3)$, $E_N(\theta_4)$, $E_N(\theta_5)$, $E_N(\theta_6)$, $E_N(\theta_7)$, and $E_N(\theta_8)$.

Now let us examine the range of Poisson's ratios that the proposed microplane formulation can generate in each case. Substituting $E_i(\theta)$ as indicated in Eqs. (12)–(14) into Eqn (11), one can obtain the following results:

$$\mathbf{E}^* = \begin{bmatrix} E_{11} & E_{12} & E_{13} & 0 & 0 & 0 \\ E_{12} & E_{11} & E_{13} & 0 & 0 & 0 \\ E_{13} & E_{13} & E_{33} & 0 & 0 & 0 \\ 0 & 0 & 0 & E_{44} & 0 & 0 \\ 0 & 0 & 0 & 0 & E_{44} & 0 \\ 0 & 0 & 0 & 0 & 0 & E_{66} \end{bmatrix} \quad (15)$$

where for case A, one can obtain the following:

$$E_{11} = [447a_1 + 3(-149 + 60\pi)a_2 + 253a_3 + (120\pi - 253)a_4] / (300\pi) \quad (16)$$

$$E_{12} = [149a_1 + (-149 + 60\pi)a_2 - 149a_3 + (149 - 60\pi)a_4] / (300\pi) \quad (17)$$

$$E_{13} = [26a_1 + (-26 + 15\pi)a_2 - 26a_3 + (26 - 15\pi)a_4] / (75\pi) \quad (18)$$

$$E_{33} = [48a_1 + (-48 + 45\pi)a_2 + 52a_3 + (-52 + 30\pi)a_4] / (75\pi) \quad (19)$$

For case B, one has the following results:

$$E_{11} = (18a_1 + 3a_2 + 10a_3 + 4a_4) / 35 \quad (20)$$

$$E_{12} = (6a_1 + a_2 - 6a_3 - a_4) / 35 \quad (21)$$

$$E_{13} = (4a_1 + 3a_2 - 4a_3 - 3a_4) / 35 \quad (22)$$

$$E_{33} = (6a_1 + 15a_2 + 8a_3 + 6a_4) / 35 \quad (23)$$

For case C, one has the following results:

$$\begin{aligned} E_{11} &= \frac{3}{8} \left[\frac{2a_3 + a_4}{(a_4 - a_3)^2} - \frac{(4a_3 - a_4)a_4 a_3^{-1/2} \arctan[(a_4 - a_3)^{1/2} a_3^{-1/2}]}{(a_4 - a_3)^{5/2}} \right. \\ &\quad \left. + \frac{2a_1 - 5a_2}{(a_2 - a_1)^2} + \frac{3a_2^2 a_1^{-1/2} \arctan[(a_2 - a_1)^{1/2} a_1^{-1/2}]}{(a_2 - a_1)^{5/2}} \right] \end{aligned} \quad (24)$$

$$\begin{aligned} E_{12} &= \frac{3}{8} \left[\frac{5a_4 - 2a_3}{3(a_4 - a_3)^2} - \frac{a_4^2 a_3^{-1/2} \arctan[(a_4 - a_3)^{1/2} a_3^{-1/2}]}{(a_4 - a_3)^{5/2}} \right. \\ &\quad \left. + \frac{2a_1 - 5a_2}{3(a_2 - a_1)^2} + \frac{a_2^2 a_1^{-1/2} \arctan[(a_2 - a_1)^{1/2} a_1^{-1/2}]}{(a_2 - a_1)^{5/2}} \right] \end{aligned} \quad (25)$$

$$\begin{aligned} E_{13} &= \frac{1}{2} \left[-\frac{2a_4 + a_3}{(a_4 - a_3)^2} + \frac{3a_4 a_3^{1/2} \arctan[(a_4 - a_3)^{1/2} a_3^{-1/2}]}{(a_4 - a_3)^{5/2}} \right. \\ &\quad \left. + \frac{2a_2 + a_1}{(a_2 - a_1)^2} - \frac{3a_2 a_1^{1/2} \arctan[(a_2 - a_1)^{1/2} a_1^{-1/2}]}{(a_2 - a_1)^{5/2}} \right] \end{aligned} \quad (26)$$

$$\begin{aligned} E_{33} &= \frac{2a_4 + a_3}{(a_4 - a_3)^2} - \frac{3a_4 a_3^{1/2} \arctan[(a_4 - a_3)^{1/2} a_3^{-1/2}]}{(a_4 - a_3)^{5/2}} \\ &\quad + \frac{a_2 - 4a_1}{(a_2 - a_1)^2} + \frac{3a_1^{3/2} \arctan[(a_2 - a_1)^{1/2} a_1^{-1/2}]}{(a_2 - a_1)^{5/2}} \end{aligned} \quad (27)$$

Note that Eqs. (24)–(27) are valid only when $a_2 > a_1$ and $a_4 > a_3$. When $a_2 < a_1$, $\arctan[(a_2 - a_1)^{1/2} a_1^{-1/2}] (a_2 - a_1)^{-5/2}$ needs to be replaced by $\text{arctanh}[(a_1 - a_2)^{1/2} a_1^{-1/2}] (a_1 - a_2)^{-5/2}$; and similarly, when $a_4 < a_3$, $\arctan[(a_4 - a_3)^{1/2} a_3^{-1/2}] (a_4 - a_3)^{-5/2}$ needs to be replaced by $\text{arctanh}[(a_3 - a_4)^{1/2} a_3^{-1/2}] (a_3 - a_4)^{-5/2}$.

in Eqs. (24)–(27). As only the range of Poisson's ratios is examined in this section, the expressions for E_{44} are not presented here.

Young's moduli and Poisson's ratios for transversely isotropic materials can be written as

$$E = (E_{11}^2 E_{33} + 2E_{13}^2 E_{12} - 2E_{11} E_{13}^2 - E_{33} E_{12}^2) / (E_{11} E_{33} - E_{13}^2) \quad (28)$$

$$E' = (E_{11}^2 E_{33} + 2E_{13}^2 E_{12} - 2E_{11} E_{13}^2 - E_{33} E_{12}^2) / (E_{11}^2 - E_{12}^2) \quad (29)$$

$$\nu = (E_{12} E_{33} - E_{13}^2) / (E_{11} E_{33} - E_{13}^2) \quad (30)$$

$$\nu' = E_{13} / (E_{11} + E_{12}) \quad (31)$$

Defining the following dimensionless variables: $t = E'/E$, $A = E_{33}/E_{11}$, $B = E_{13}/E_{11}$, and $C = E_{12}/E_{11}$, one has

$$t = E'/E = (A - B^2) / (1 - C^2) \quad (32)$$

$$\nu = (CA - B^2) / (A - B^2) \quad (33)$$

$$\nu' = B / (1 + C) \quad (34)$$

Furthermore, by setting $\alpha = a_2/a_1$, $\beta = a_3/a_1$, and $\gamma = a_4/a_1$, one can plot the values of $t(\alpha, \beta, \gamma)$, $\nu(\alpha, \beta, \gamma)$, and $\nu'(\alpha, \beta, \gamma)$ for any $\alpha > 0$, $\beta > 0$, and $\gamma > 0$. Calculated from 10^8 randomly generated positive real numbers used as α , β , or γ , the results for each case are shown in Fig. 3 with different values of t indicated by different colors. (The figures appear in color in the electronic version of this article.) It can be seen that the ranges of ν , ν' , and t generated by case B are only slightly larger than those obtained from case A, but significantly smaller than those obtained from case C and case D.

To further compare the possible range of Poisson's ratios obtained from each case, one can obtain the contour plot of t for each case. Substituting Eqs. (32) and (34) into Eq. (33), the function of $\nu = \nu(\nu', t, C)$ can be obtained as follows:

$$\nu = C - \nu'^2(1 + C)/t \quad (35)$$

To obtain the upper and lower bounds of ν for every possible value of ν' with different values of t , one needs to maximize and minimize $\nu(\alpha, \beta, \gamma)$, for any $\alpha > 0$, $\beta > 0$, and $\gamma > 0$, subject to the constraints that $\nu'(\alpha, \beta, \gamma) = \nu'_0$ and $t(\alpha, \beta, \gamma) = t_0$. The results for each case are shown in Fig. 2 with different values of t indicated by different colors, and they are compared with the thermodynamic restrictions on elastic constants of transversely isotropic materials obtained from Eqs. (2)–(4). As shown in Fig. 2, although the largest ranges of ν and ν' are generated by case D, the results obtained are still not exhaustive, because for case D, it was assumed that the modulus values at each microplane orientation are a function of θ only, which put a restriction on the possible range of Poisson's ratios.

Since Fig. 2 confirms that case C and case D generate the largest ranges of ν , ν' , and t , they will be adopted for the numerical modeling of transversely isotropic elasticity of quasi-brittle materials in this study. Two examples are given as shown below.

6.1 Elastic Microplane Model Formulation for Shale.

Adequate knowledge and prediction of mechanical properties of shale are pivotal to the success in many fields of petroleum engineering, ranging from seismic exploration, to well drilling and production, and to the design of hydraulic fractures. Shale is best described as transversely isotropic quasi-brittle material with the symmetric axes being perpendicular to bedding. In laboratory measurements of shale, high magnitude of anisotropy was reported for both static [43] and dynamic [44] conditions, which cannot be neglected in shale modeling. Neglecting shale anisotropy may lead to incorrect estimates of rock and fluid properties, fracture aperture, fracture containment, and stress or stress changes resulting from production. To the best of the authors' knowledge, a microplane




Fig. 3 The values of $t(\alpha, \beta, \gamma)$, $\nu(\alpha, \beta, \gamma)$, and $\nu'(\alpha, \beta, \gamma)$ for any $\alpha > 0$, $\beta > 0$, and $\gamma > 0$ for each case with different values of t indicated by different colors. The figure appears in color in the electronic version of this article.

model to completely characterize the transversely isotropic elastic behavior of shale has not yet been developed.

Due to the presence of bedding-parallel weakness planes, shales are in general stiffer along the bedding planes than perpendicular to bedding, i.e., $E'/E < 1$. Figure 4 plots the ranges of ν and ν' obtained from microplane model based on case C for seven different values of E'/E when $0 < E'/E \leq 1$. The ranges of ν and ν' for various types of shale provided by the existing literature [45–50] are also plotted in Fig. 4. It can be seen that the ranges of ν and ν' for most types of shale fall within the microplane simulation region. The predicted Poisson's ratios in Fig. 4 are reasonable, as according to the existing literature [45–50], the ratio of E'/E is about 0.5 for Boryeong shale, 0.6–1.0 for Barnett shale, 0.4–0.6 for Haynesville shale, and approximately 0.5 for Eagle Ford shale. The ranges of ν and ν' based on case D are also plotted in Fig. 4 for comparison. It shows that the possible range of Poisson's ratios obtained from case D is much larger than those obtained from case C.

One can take Boryeong shale as an example, which has been extensively investigated in the literature. The experimental data on the five elastic constants of Boryeong shale are provided by Cho et al. [47], as shown in Table 1. Based on the experimental data, one has $E = 37.3$ GPa, $E' = 18.4$ GPa, $\nu = 0.15$, $\nu' = 0.16$, and $G = 12.0$ GPa, and the elastic stiffness matrix, \mathbf{E} , reads

$$\mathbf{E} = \begin{bmatrix} 41.2104 & 8.7756 & 7.9978 & 0 & 0 & 0 \\ 8.7756 & 41.2104 & 7.9978 & 0 & 0 & 0 \\ 7.9978 & 7.9978 & 20.9593 & 0 & 0 & 0 \\ 0 & 0 & 0 & 24.0000 & 0 & 0 \\ 0 & 0 & 0 & 0 & 24.0000 & 0 \\ 0 & 0 & 0 & 0 & 0 & 32.4348 \end{bmatrix} \text{ GPa} \quad (36)$$

By adopting the formulation provided by case C, and determining the unknown parameters a_i ($i = 1, 2, 3, 4$) by minimizing the Frobenius norm $\sqrt{\sum_{i,j} |E_{ij}^* - E_{ij}|^2}$, where \mathbf{E}^* is defined in Eq. (11), one obtains $a_1 = 0.0132 \text{ GPa}^{-1}$, $a_2 = 0.0408 \text{ GPa}^{-1}$, $a_3 = 0.0289 \text{ GPa}^{-1}$, and $a_4 = 0.6227 \text{ GPa}^{-1}$, which gives the following results:

$$\mathbf{E}^* = \begin{bmatrix} 41.4836 & 8.8028 & 7.5865 & 0 & 0 & 0 \\ 8.8028 & 41.4836 & 7.5865 & 0 & 0 & 0 \\ 7.5865 & 7.5865 & 20.9401 & 0 & 0 & 0 \\ 0 & 0 & 0 & 24.1149 & 0 & 0 \\ 0 & 0 & 0 & 0 & 24.1149 & 0 \\ 0 & 0 & 0 & 0 & 0 & 32.0101 \end{bmatrix} \text{ GPa} \quad (37)$$

It can be seen that a good match between \mathbf{E}^* and \mathbf{E} has been obtained. Based on Eq. (14), one can plot the curves for the values and the ratios of E_i ($i = N, M, L$) as a function of θ , as shown in Fig. 5. Figure 6 shows the variation of apparent Young's modulus with anisotropy angle in comparison with experimental data provided by Cho et al. [47].

Alternatively, case D can also be applied. The unknown parameters $E_M(\theta_1)$, $E_M(\theta_2)$, $E_M(\theta_3)$, $E_M(\theta_4)$, $E_M(\theta_5)$, $E_M(\theta_6)$, $E_M(\theta_7)$, $E_M(\theta_8)$, $E_N(\theta_1)$, $E_N(\theta_2)$, $E_N(\theta_3)$, $E_N(\theta_4)$, $E_N(\theta_5)$, $E_N(\theta_6)$, $E_N(\theta_7)$, and $E_N(\theta_8)$ can be determined by minimizing the Frobenius norm $\sqrt{\sum_{i,j} |E_{ij}^* - E_{ij}|^2}$. One obtains the following results:

$$\mathbf{E}^* = \begin{bmatrix} 41.2104 & 8.7756 & 7.9978 & 0 & 0 & 0 \\ 8.7756 & 41.2104 & 7.9978 & 0 & 0 & 0 \\ 7.9978 & 7.9978 & 20.9593 & 0 & 0 & 0 \\ 0 & 0 & 0 & 24.0000 & 0 & 0 \\ 0 & 0 & 0 & 0 & 24.0000 & 0 \\ 0 & 0 & 0 & 0 & 0 & 32.4348 \end{bmatrix} \text{ GPa} \quad (38)$$

In this case, an exact match is obtained. The results for the values and the ratios of E_i ($i = N, M, L$) as a function of θ are shown in Fig. 5.

6.2 Elastic Microplane Model Formulation for Rigid Polymeric Foams. Foamed plastics, such as polyurethane, polyvinyl chloride (PVC), polystyrene, polypropylene, epoxy, phenol-formaldehyde, cellulose acetate, and silicone, are widely used as core materials for sandwich structures in automotive and aerospace industries due to their light weight and high specific stiffness. They are good heat insulators by virtue of the low conductivity of the gas contained in the cells; they have a higher ratio of flexural modulus to density than before foaming; and they




Fig. 4 The ranges of ν and ν' obtained from microplane model based on case C and case D when $0 < E'/E \leq 1$, respectively. The ranges of ν and ν' for various types of shale studied by the existing literature [40–45] are also plotted. The figure appears in color in the electronic version of this article.




Fig. 5 The results for the values and the ratios of E_i ($i = N, M, L$) as a function of θ obtained from case C and case D for example A, respectively




Fig. 6 The variation of apparent Young's modulus with anisotropy angle in comparison with experimental data provided by Cho et al. [42]

achieve a greater load-bearing capacity per unit weight, as well as greater energy storage and energy dissipation capacities [3,51,52].

However, most of the polymeric foams usually show an anisotropic behavior, which complicates the numerical modeling of such materials. For simplicity, the elastic response of polymeric foams is usually regarded as transversely isotropic: during the foaming process, viscous forces cause the cells to be elongated in the rise direction, and therefore the material response in this direction is stiffer, i.e., $E'/E > 1$. The ratio of the modulus in the rise direction to that in the perpendicular-to-rise direction is indicative of the extent of elongation of the cells.

Let us take rigid PVC foams as an example. The experimental data on the five elastic constants of DIAB Divinycell H60 are provided by the DIAB group [53] and Tita et al. [54], as shown in Table 2. Based on the experimental data, one has $E = 16.0$ GPa, $E' = 32.0$ GPa, $\nu = 0.29$, $\nu' = 0.28$, and $G = 15.0$ GPa, and the elastic stiffness matrix, \mathbf{E} , reads:

Table 1 The five elastic constants of Boryeong shale

Elastic constants	Experimental data [42]	Data generated by microplane model
Young's modulus parallel to bedding, E (GPa)	34–45.8	37.30
Young's modulus perpendicular to bedding, E' (GPa)	16.5–20.5	18.40
Poisson's ratio parallel to bedding, ν	0.13–0.23	0.15
Poisson's ratio perpendicular to bedding, ν'	0.14–0.23	0.16
Shear modulus, G (GPa)	6.2–12.0	12.00

$$\mathbf{E} = \begin{bmatrix} 18.8678 & 6.4647 & 7.0931 & 0 & 0 & 0 \\ 6.4647 & 18.8678 & 7.0931 & 0 & 0 & 0 \\ 7.0931 & 7.0931 & 35.9721 & 0 & 0 & 0 \\ 0 & 0 & 0 & 30.0000 & 0 & 0 \\ 0 & 0 & 0 & 0 & 30.0000 & 0 \\ 0 & 0 & 0 & 0 & 0 & 12.4031 \end{bmatrix} \text{ GPa} \quad (39)$$

By adopting the formulation provided by case C, and determining the unknown parameters a_i ($i = 1, 2, 3, 4$) by minimizing $\sqrt{\sum_{i,j} |E_{ij}^* - E_{ij}|^2}$, one has $a_1 = 0.0378 \text{ GPa}^{-1}$, $a_2 = 0.0109 \text{ GPa}^{-1}$, $a_3 = 1.2882 \text{ GPa}^{-1}$, and $a_4 = 0.0026 \text{ GPa}^{-1}$, which gives the following results:

$$\mathbf{E}^* = \begin{bmatrix} 18.6261 & 5.8339 & 7.7705 & 0 & 0 & 0 \\ 5.8339 & 18.6261 & 7.7705 & 0 & 0 & 0 \\ 7.7705 & 7.7705 & 35.9102 & 0 & 0 & 0 \\ 0 & 0 & 0 & 30.0000 & 0 & 0 \\ 0 & 0 & 0 & 0 & 30.0000 & 0 \\ 0 & 0 & 0 & 0 & 0 & 12.8046 \end{bmatrix} \text{ GPa} \quad (40)$$

It can be seen that the match between \mathbf{E} and \mathbf{E}^* obtained from case C is not very accurate but still satisfactory. Figure 7 plots the curves for the values and the ratios of E_i ($i = N, M, L$) as a function of θ .

Table 2 The five elastic constants of DIAB Divinycell H60

Elastic constants	Experimental data [48,49]	Data generated by microplane model
Young's modulus in transverse direction, E (GPa)	13.0–19.0	16.0
Young's modulus in rise direction, E' (GPa)	31.0–33.0	32.0
Poisson's ratio in the plane perpendicular to rise direction, ν	0.29–0.31	0.29
Poisson's ratio in rise direction, ν'	0.04–0.44	0.28
Shear modulus, G (GPa)	15.0–20.0	15.0

For case D, the optimized microplane parameters give

$$\mathbf{E}^* = \begin{bmatrix} 18.8678 & 6.4647 & 7.0931 & 0 & 0 & 0 \\ 6.4647 & 18.8678 & 7.0931 & 0 & 0 & 0 \\ 7.0931 & 7.0931 & 35.9721 & 0 & 0 & 0 \\ 0 & 0 & 0 & 30.0000 & 0 & 0 \\ 0 & 0 & 0 & 0 & 30.0000 & 0 \\ 0 & 0 & 0 & 0 & 0 & 12.4031 \end{bmatrix} \text{ GPa} \quad (41)$$

which basically coincides with \mathbf{E} . The results for the values and the ratios of E_i ($i = N, M, L$) as a function of θ are shown in Fig. 7.

7 Comparison Between Microplane Model With Orientation Dependent Moduli and Spectral Stiffness Microplane Model

Note that Eqs. (12)–(14) are just assumptions in the form of E_i ($i = N, M, L$), and the actual form of E_i can be obtained only when




Fig. 7 The results for the values and the ratios of E_i ($i = N, M, L$) as a function of θ obtained from case C and case D for example B, respectively

the microplane model is under double constraint, which is derived through the spectral stiffness microplane model. It is worth then studying the accuracy with which the non-spectral formulation approximates the actual microplane stress distribution.

By taking the Boryeong shale again as reference, the distributions of the normal strain component, ε_N , on a generic microplane

sphere caused by different types of macroscopic strains are shown in Fig. 8. It has six subfigures, corresponding to the distribution of ε_N on the microplane sphere under uniaxial strains ε_{11} , ε_{22} , and ε_{33} , and shear strains ε_{23} , ε_{13} , and ε_{12} , respectively. Each subfigure includes one three-dimensional plot and three contours plots on the x_1 - x_3 plane, the x_2 - x_3 plane, and the x_1 - x_2 plane, respectively.




Fig. 8 The distribution of the normal strain component, ε_N , on a generic microplane sphere caused by different types of macroscopic strains for the Boryeong shale with $E = 37.3$ GPa, $E' = 18.4$ GPa, $\nu = 0.15$, $\nu' = 0.16$, and $G = 12.0$ GPa

In a similar manner, the distributions of the normalized normal stress component, σ_N , are shown in Fig. 9. For the purpose of comparison, Fig. 10 plots the distributions of the normalized normal stress component σ_N based on the assumption that $\sigma_N = E_N \varepsilon_N$, where $E_N = 1/(a_1 \sin^2 \theta + a_2 \cos^2 \theta)$ as given in case C. It can be seen that, while not an exact match, the stress distribution obtained from the formulation in case C matches closely with the actual stress distribution. The deviation of σ_N based on

orientation variation microplane model from the one based on spectral stiffness microplane model is typically in the range of 11–28%: the deviation under uniaxial strain ε_{11} or ε_{22} is less than 20%; the deviation under uniaxial strain ε_{33} is less than 28%; and the deviation under shear strain ε_{23} , ε_{13} , or ε_{12} is less than 11%.

The actual E_N can be obtained by $E_N = \sigma_N / \varepsilon_N$, where ε_N and σ_N are given as follows:





Fig. 9 The distribution of the normalized normal stress component, σ_N , on a generic microplane sphere caused by different types of macroscopic strains for the Boryeong shale with $E = 37.3$ GPa, $E' = 18.4$ GPa, $\nu = 0.15$, $\nu' = 0.16$, and $G = 12.0$ GPa


$$\begin{aligned}\varepsilon_N = & \sin^2 \theta \left[\gamma_1 (\cos^2 \phi - \sin^2 \phi) + 2\sqrt{2}\varepsilon_6 \sin \phi \cos \phi \right] \\ & + \gamma_2 \left(-\sin \omega \sin^2 \theta / \sqrt{2} + \cos \omega \cos^2 \theta \right) \\ & + \gamma_3 \left(\cos \omega \sin^2 \theta / \sqrt{2} + \sin \omega \cos^2 \theta \right) \\ & + 2\sqrt{2} \sin \theta \cos \theta (\varepsilon_4 \sin \phi + \varepsilon_5 \cos \phi)\end{aligned}\quad (42)$$

$$\begin{aligned}\sigma_N = & \lambda_1 \sin^2 \theta \left[\gamma_1 (\cos^2 \phi - \sin^2 \phi) + 2\sqrt{2}\varepsilon_6 \sin \phi \cos \phi \right] \\ & + \lambda_2 \gamma_2 \left(-\sin \omega \sin^2 \theta / \sqrt{2} + \cos \omega \cos^2 \theta \right) \\ & + \lambda_3 \gamma_3 \left(\cos \omega \sin^2 \theta / \sqrt{2} + \sin \omega \cos^2 \theta \right) \\ & + 2\sqrt{2} \lambda_4 \sin \theta \cos \theta (\varepsilon_4 \sin \phi + \varepsilon_5 \cos \phi)\end{aligned}\quad (43)$$


Microplane Stress under Uniaxial Strain ε_{11}




Microplane Stress under Uniaxial Strain ε_{22}




Microplane Stress under Uniaxial Strain ε_{33}



Microplane Stress under Shear Strain ε_{23}



Microplane Stress under Shear Strain ε_{13}



Microplane Stress under Shear Strain ε_{12}




Fig. 10 The distributions of the normalized normal stress component σ_N based on the assumption that $\sigma_N = E_N \varepsilon_N$, where $E_N = 1/(a_1 \sin^2 \theta + a_2 \cos^2 \theta)$ as given in case C, caused by different types of macroscopic strains for the Boryeong shale with $E = 37.3$ GPa, $E' = 18.4$ GPa, $\nu = 0.15$, $\nu' = 0.16$, and $G = 12.0$ GPa




Fig. 11 (a) plots of the actual E_N under $\varepsilon_{11} = \varepsilon_{22} = \varepsilon_{33} = 1$ and $\varepsilon_{13} = \varepsilon_{23} = \varepsilon_{12} = 0$, (b) plots of the actual E_N under $\varepsilon_{11} = \varepsilon_{22} = \varepsilon_{33}/4 = 1$ and $\varepsilon_{13} = \varepsilon_{23} = \varepsilon_{12} = 0$, (c) plots of the actual E_N under $\varepsilon_{11} = \varepsilon_{22} = \varepsilon_{33} = \varepsilon_{12} = 1$ and $\varepsilon_{13} = \varepsilon_{23} = 0$, and (d) plots of $E_N = 1/(a_1 \sin^2 \theta + a_2 \cos^2 \theta)$ as assumed in case C

with $\gamma_1 = (\varepsilon_1 - \varepsilon_2)/2$, $\gamma_2 = -\sin \omega (\varepsilon_1 + \varepsilon_2)/\sqrt{2} + \varepsilon_3 \cos \omega$, and $\gamma_3 = \cos \omega (\varepsilon_1 + \varepsilon_2)/\sqrt{2} + \varepsilon_3 \sin \omega$. Figures 11(a)–11(c) plot the actual E_N under different macroscopic strains, and Fig. 11(d) plots $E_N = 1/(a_1 \sin^2 \theta + a_2 \cos^2 \theta)$ as assumed in case C. It can be seen that while the E_N assumed in case C is a function of θ only, the actual E_N is a function of not only θ but also ϕ and the macroscopic strain.

8 Concluding Remarks

This contribution has studied the extension of the microplane formulation to transversely isotropic materials such as shale rock, polymeric foams, and composites among others. It has been demonstrated that, while the spectral stiffness decomposition provides the only rigorous approach for the description of microplane strains and stresses in transverse isotropy, an approximation almost as accurate could be obtained by making the elastic microplane moduli a function of the microplane orientation. It was shown that the latter approach can span a broad range of macroscopic elastic properties compared to the thermodynamic restrictions on the anisotropic parameters. Further, the approximated functions have the advantage to provide a diagonal microplane elastic matrix which makes easier to guarantee work consistency

and, more importantly, makes the formulation of inelastic boundaries easier.

Acknowledgment

C. Jin thanks the start-up funds provided by Department of Mechanical Engineering at State University of New York at Binghamton. G. Cusatis thanks the funding support from U.S. National Science Foundation through Grant No. CMMI-1435950 to Northwestern University.

References

- [1] Lemaitre, J., and Desmorat, R., 2005, *Engineering Damage Mechanics: Ductile, Creep, Fatigue and Brittle Failures*, Springer Verlag, New York.
- [2] Bažant, Z. P., and Planas, J., 1997, *Fracture and Size Effect in Concrete and Other Quasibrittle Materials*, CRC Press, Boca Raton, FL.
- [3] Brocca, M., Bažant, Z. P., and Daniel, I. M., 2001, "Microplane Model for Stiff Foams and Finite Element Analysis of Sandwich Failure by Core Indentation," *Int. J. Solids Struct.*, **38**(44–45), pp. 8111–8132.
- [4] Bažant, Z. P., and Oh, B.-H., 1983, "Microplane Model for Fracture Analysis of Concrete Structures," *Symposium on the Interaction of Non-Nuclear Munitions With Structures*, Colorado Springs, CO, pp. 49–53.
- [5] Bažant, Z. P., and Oh, B.-H., 1985, "Microplane Model for Progressive Fracture of Concrete and Rock," *J. Eng. Mechanics, Trans. ASCE* **111**(4), pp. 559–582.
- [6] Bažant, Z. P., Caner, F. C., Carol, I., Adley, M. D., and Akers, S. A., 2000, "Microplane Model M4 for Concrete: I. Formulation With Work-Conjugate Deviatoric Stress," *J. Eng. Mechanics, Trans. ASCE*, **126**(9), pp. 944–953.

- [7] Bažant, Z. P., Adley, M. D., Carol, I., Jirásek, M., Akers, S. A., Rohani, B., Cargile, J. D., and Caner, F. C., 2000, "Large-Strain Generalization of Microplane Model for Concrete and Application," *J. Eng. Mechanics, Trans. ASCE*, **126**(9), pp. 971–980.
- [8] Bažant, Z. P., and Prat, P. C., 1988, "Microplane Model for Brittle Plastic Material: I. Theory," *J. Eng. Mech. ASCE*, **114**(10), pp. 1672–1688.
- [9] Bažant, Z. P., Xiang, Y., and Prat, P. C., 1996, "Microplane Model for Concrete. I. Stress-Strain Boundaries and Finite Strain," *J. Eng. Mech. ASCE*, **122**(3), pp. 245–254.
- [10] Caner, F. C., and Bažant, Z. P., 2000, "Microplane Model M4 for Concrete. II: Algorithm and Calibration," *J. Eng. Mech. Trans. ASCE*, **126**(9), pp. 954–961.
- [11] Bažant, Z. P., Di Luzio, G., 2004, "Nonlocal Microplane Model With Strain-Softening Yield Limits," *Int. J. Solids Struct.*, **41**(24–25), pp. 7209–7240.
- [12] Bažant, Z. P., and Caner, F. C., 2005, "Microplane Model M5 With Kinematic and Static Constraints for Concrete Fracture and Anelasticity. I Theory," *J. Eng. Mech. ASCE*, **130**(1), pp. 31–40.
- [13] Bažant, Z. P., and Caner, F. C., 2005, "Microplane Model M5 With Kinematic and Static Constraints for Concrete Fracture and Anelasticity. II Computation," *J. Eng. Mech. ASCE*, **130**(1), pp. 41–47.
- [14] Bažant, Z. P., and Zi, G., 2003, "Microplane Constitutive Model for Porous Isotropic Rock," *Int. J. Numer. Anal. Methods Geomech.*, **27**(1), pp. 25–47.
- [15] Bažant, Z. P., and Prat, P. C., 1987, "Creep of Anisotropic Clay: New Microplane Model," *J. Eng. Mech. ASCE*, **113**(7), pp. 1000–1064.
- [16] Brocca, M., and Bažant, Z. P., 2001, "Microplane Finite Element Analysis of Tube-Squash Test of Concrete With Angle up to 70°," *Int. J. Numer. Methods Eng.*, **52**(10), pp. 1165–1188.
- [17] Beghini, A., Bažant, Z. P., Zhou, Y., Gouirand, O., and Caner, F. C., 2007, "Microplane Model M5f for Multiaxial Behavior and Fracture of Fiber Reinforced Concrete," *ASCE J. Eng. Mech.*, **133**(1), pp. 66–75.
- [18] Caner, F. C., and Bažant, Z. P., 2011, "Microplane Model M6f for Fiber Reinforced Concrete," XI Int. Conference on Computational Plasticity Fundamentals and Applications, COMPLAS 2011, Barcelona, Spain, pp. 796–807.
- [19] Caner, F., and Bažant, Z. P., 2013, "Microplane Model M7 for Plain Concrete. I: Formulation," *J. Eng. Mech.*, **139**(12), pp. 1714–1723.
- [20] Caner, F., and Bažant, Z. P., 2013, "Microplane Model M7 for Plain Concrete. II: Calibration and Verification," *J. Eng. Mech.*, **139**(12), pp. 1724–1735.
- [21] Kirane, K., and Bažant, Z. P., 2015, "Microplane Damage Model for Fatigue of Quasi-Brittle Materials: Sub-Critical Crack Growth, Lifetime and Residual Strength," *Int. J. Fatigue*, **70**, pp. 93–105.
- [22] Cusatis, G., and Zhou, X., 2014, "High-Order Microplane Theory for Quasi-Brittle Materials With Multiple Characteristic Lengths," *J. Eng. Mech.*, **140**(7), p. 04014046.
- [23] Mohr, O., 1900, "Welche Umstände bedingen die Elastizitätsgrenze und den Bruch eines Materials," *Z. Ver. Dtsch. Ing.*, **46**, pp. 1524–1530; 1572–1577.
- [24] Taylor, G. I., 1938, "Plastic Strain in Metals," *J. Inst. Metals*, **62**, pp. 307–324.
- [25] Batdorf, S. B., and Budiansky, B., 1949, "A Mathematical Theory of Plasticity Based on the Concept of Slip," National Advisory Committee for Aeronautics, Washington, DC, *Technical Note No. 1871*.
- [26] Brocca, M., and Bažant, Z. P., 2000, "Microplane Constitutive Model and Metal Plasticity," *ASME Appl. Mech. Rev.*, **53**(10), pp. 265–281.
- [27] Cusatis, G., Beghini, H., and Bažant, Z. P., 2008, "Spectral Stiffness Microplane Model for Quasibrittle Composite Laminates—Part I: Theory," *ASME J. Appl. Mech.*, **75**(2), p. 021009.
- [28] Chang, K. T., and Sture, S., 2006, "Microplane Modeling of Sand Behavior Under Non-Proportional Loading," *Comput. Geotech.*, **33**(3), pp. 177–178.
- [29] Brocca, M., Brinson, L. C., and Bažant, Z. P., 2002, "Three-Dimensional Constitutive Model for Shape Memory Alloys Based on Microplane Model," *J. Mech. Phys. Solids*, **50**(5), pp. 1051–1077.
- [30] Cusatis, G., Beghini, H., and Bažant, Z. P., 2008, "Spectral Stiffness Microplane Model for Quasibrittle Composite Laminates—Part II: Calibration and Validation," *ASME J. Appl. Mech.*, **75**(2), p. 021010.
- [31] Caner, F. C., Bažant, Z. P., Hoover, C., Waas, A., and Shahwan, K., 2011, "Microplane Model for Fracturing Damage of Triaxially Braided Fiber-Polymer Composites," *ASME J. Eng. Mater. Technol.*, **133**(2), p. 021024.
- [32] Cusatis, G., Mencarelli, A., Pelessone, D., and Baylot, J. T., 2011, "Lattice Discrete Particle Model (LDPM) for Failure Behavior of Concrete. II: Calibration and Validation," *Cem. Concr. Compos.*, **33**(9), pp. 891–905.
- [33] Cusatis, G., Pelessone, D., and Mencarelli, A., 2011, "Lattice Discrete Particle Model (LDPM) for Failure Behavior of Concrete. I: Theory," *Cem. Concr. Compos.*, **33**(9), pp. 881–890.
- [34] Bažant, Z. P., and Kim, J.-K., 1986, "Creep of Anisotropic Clay: Microplane Model," *J. Geotech. Eng. ASCE*, **112**(4), pp. 458–475.
- [35] Carol, I., and Bažant, Z. P., 1997, "Damage and Plasticity in Microplane Theory," *Int. J. Solids Struct.*, **34**(29), pp. 3807–3835.
- [36] Elbing, K., 1994, *Foundation of Anisotropy for Exploration Seismic*, Pergamon Press, Oxford, UK.
- [37] Gurtin, M. E., 1972, "The Linear Theory of Elasticity," *Handbuch der Physik*, Vol. VI/2, pp. 1–296.
- [38] Theocaris, P. S., and Sokolis, D. P., 1998, "Spectral Decomposition of the Compliance Tensor for Anisotropic Plates," *J. Elasticity*, **51**(2), pp. 89–103.
- [39] Theocaris, P. S., and Sokolis, D. P., 2000, "Spectral Decomposition of the Compliance Fourth-Rank Tensor for Orthotropic Materials," *Arch. Appl. Mech.*, **70**(4), pp. 289–306.
- [40] Theocaris, P. S., and Sokolis, D. P., 1999, "Spectral Decomposition of the Linear Elastic Tensor for Monoclinic Symmetry," *Acta Crystallogr.*, **A55**(4), pp. 635–647.
- [41] Bažant, Z. P., and Oh, B.-H., 1986, "Efficient Numerical Integration on the Surface of a Sphere," *Z. Angew. Math. Mech.*, **66**(1), pp. 37–49.
- [42] Stroud, A. H., 1971, *Approximate Calculation of Multiple Integrals*, Prentice-Hall, Englewood Cliffs, NJ.
- [43] Amadei, B., 1996, "Importance of Anisotropy When Estimation and Measuring In Situ Stresses in Rock," *Int. J. Rock Mech. Min. Sci. Geotech. Abstr.*, **33**(3), pp. 293–326.
- [44] Wang, Z., 2001, "Fundamentals of Seismic Rock Physics," *Geophysics*, **66**(2), pp. 398–412.
- [45] Lin, W., 1981, "Mechanical Behavior of Mesaverde Shale and Sandstone at High Pressure," *SPE/DOE Low Permeability Gas Reservoirs Symposium*, Denver, CO, May 27–29, Paper No. SPE/DOE 9835.
- [46] Bossart, P., 2011, "Characteristics of the Opalinus Clay at Mont Terri," *Mont Terri Project*, Wabern Switzerland.
- [47] Cho, J. W., Kim, H., Jeon, S., and Min, K. B., 2012, "Deformation and Strength Anisotropy of Asan Gneiss, Boryeong Shale, and Yeoncheon Schist," *Int. J. Rock Mech. Min. Sci.*, **50**, pp. 158–169.
- [48] Sone, H., and Zoback, M. D., 2013, "Mechanical Properties of Shale Gas Reservoir Rocks—Part 1: Static and Dynamic Elastic Properties and Anisotropy," *Geophysics*, **78**(5), pp. D381–D392.
- [49] Sone, H., 2012, "Mechanical Properties of Shale Gas Reservoir Rocks and its Relation to the In-Situ Stress Variation Observed in Shale Gas Reservoirs," Ph.D. thesis, Stanford University, Stanford, CA.
- [50] Waters, G. A., Lewis, R. E., and Bentley, D., 2011, "The Effect of Mechanical Properties Anisotropy in the Generation of Hydraulic Fractures in Organic Shales," *SPE Annual Technical Conference and Exposition*, Denver, CO, Oct. 30–Nov. 2, Paper No. SPE 146776.
- [51] Gibson, L. J., 1989, "Modeling the Mechanical Behavior of Cellular Materials," *Mater. Sci. Eng. A*, **110**, pp. 1–36.
- [52] Gibson, L. J., and Ashby, M. F., 1997, *Cellular Solids: Structure and Properties*, Pergamon Press, Oxford, UK.
- [53] DIAB Group, 2014, "Technical Data for Divinycell H Grade," *DIAB*, Laholm, Sweden.
- [54] Tita, V., Caliri, M. F., Angelico, R. A., and Canto, R. B., 2012, "Experimental Analyses of the Poly(vinyl chloride) Foams' Mechanical Anisotropic Behavior," *Polym. Eng. Sci.*, **52**(12), pp. 2654–2663.